

# Pure Nickel Special

## Product Description

Never-Seez<sup>®</sup> Pure Nickel Special is a superior, high temperature anti-seize and extreme pressure lubricant containing flake particles of pure nickel, graphite and other additives in a special grease carrier found to enhance anti-seize performance.

Recommended for use when applications prohibit the presence of copper, especially when resistance to corrosive acidic and caustic solutions is required.

## Product Benefits

- Excellent heat dispersing qualities
- Minimizes corrosion
- Prevents seizure at high temperatures
- Resists galvanic action between dissimilar metals
- Enables fast disassembly-even after high temperature exposure
- Prevents galling on steel to stainless steel, titanium, magnesium and other hard metals
- Resists alkaline solutions, most chemical and acid vapors, road salt, steam, salt water, ionized water

## Product Applications

- Fittings, fasteners exposed to high temperatures in steel mills, power plants, nuclear plants
- Stainless steel pipe fittings, flanges, pump fittings
- Fasteners in exhaust manifolds and boilers
- Steam generators
- Assembly of dissimilar metals

## Limitations

- Never-Seez<sup>®</sup> Pure Nickel Special is not recommended for high speed bearing applications. Never-Seez<sup>®</sup> Red Bearing Lubricant is suggested for these applications.
- In applications where indirect food contact is possible, use USDA approved Never-Seez<sup>®</sup> White Food Grade.

## Other Anti-Seize Lubricants

- Regular Grade
- High Temperature Bearing Lubricant
- High Temp Stainless
- Pipe Compound with Teflon<sup>®</sup>
- High Temp Stainless, Nuclear Certified
- Marine Grade
- Blue Moly Lubricant
- Black Moly
- Red Bearing Lubricant
- White Food Grade with PTFE
- Pure Nickel Special, Nuclear Grade
- Heavy Metal Free



## Technical Specifications

Color	Silver
Temperature Range, °F (°C)	-22°F to 2400°F (-30°C to 1316°C)
Thickener Type	Lithium Soap
Particle Size, mil (microns)	2 maximum (50 µ)
Density, (g/cm <sup>3</sup> )	1.24 - 1.3

		ASTM Test Method
Flash Point, °F (°C)	>475°F (>246°C)	D-92
Copper Corrosion Test @ 212°F (100°C), 24 hrs.	No corrosion	D-130
Worked Penetration: 60 strokes @ 77°F (25°C)	260-310	D-217
NLGI Grade	1/2	D-217
Dropping Point, °F (°C)	360°F (182°C)	D-566
Water Washout, % loss @ 100°F @ 175°F	<2 <5	D-1264
Coefficient of Friction @ 167°F (75°C), Four Ball	0.092	D-2266
Torque Coefficient, k factor	0.158	
Four Ball EP Load Wear Index	68	D-2596
Last Non-seizure Load (scar)	79 kgf (0.59 mm)	
Last Seizure Load (scar)	250 kgf (1.46 mm)	
Weld Load	315 kgf	

## Electrical Properties

		D-150
Cycles	Dissipation Factor	Dielectric Constant
1,000	0.0227	10.56
10,000	0.0347	10.26

**Ingredients:** A special, high-quality grease with graphite, pure nickel and other additives. Contains no molybdenum disulfide, lead, or mercury except as trace elements.

**Shelf Life:** Never-Seez® Pure Nickel Special compound does not deteriorate with age when stored unopened at temperatures below 120°F (49°C). Quality and performance are guaranteed for five years from the date of manufacture on unopened containers.

**Use in accordance with Material Safety Data Sheet.**

**Ordering Information:**

NEVER-SEEZ® PURE NICKEL SPECIAL

STOCK NUMBER	DESCRIPTION	SIZE
NSN-165	Flat Top	1 lb.
NSN-8	Flat Top	8 lb.
NSBT-8N	Brush Top	8 oz.
NSBT-16N	Brush Top	1 lb.
NSN-42B	Pail	42 lbs.
NSN-130B	Drum	130 lbs.
NSN-425B	Drum	425 lbs.



**Aerospheres**  
AGC AEROSPACE & DEFENSE

**Bostik, Inc.**  
211 Boston Street  
Middleton, MA 1949-2128 USA  
Technical Service: 888-603-8558  
FAX: 978-750-7293  
<http://www.bostik-us.com>

**IMPORTANT NOTICE**

All statements, technical information and recommendations set forth herein are based on tests which Bostik, Inc. believes to be reliable. However, Bostik does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik's order acknowledgment. Bostik, Inc. warrants that the product conforms with Bostik's written specifications, and is free from defects. BOSTIK, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES.